

ABSTRACT OF THE DISCLOSURE

A gap layer of a thin-film magnetic head is formed of NiP. The P content of the NiP gap layer is controlled to be within the range of 11 mass percent to 14 mass percent so that the gap layer is nonmagnetic.

TOP SECRET 9225350